

(L871)

23 May 1892.

17, CARLYLE SQUARE,  
S.W.

Dear General Pitt Rivers

I enclose Gowland's  
receipt for the bath to  
prevent iron implements  
from disintegration - It  
has been most successful  
with his Japanese iron,

Your enamelled pendant  
seems certainly to be  
Dr. Philippa, as I  
thought - eg. 4 lions

STANDARD EXHIBIT

W. 2

rampant.

Yours very truly

Charles H. Reed

Bath for Iron implements (W. Gowland)

1oz. of Sodium carbonate to 1½ pint of water

Soak for three days - then wash in running water for a week to a fortnight

It is essential that all the sodium should be washed out from the iron.

1871